

## Trade Select™ ThermalLiner™

Product Code: TSTB4

### Roof and wall shed insulation

For residential homes or commercial sheds

Extra R-Value



Trade Select™ ThermalLiner™ is an Extra Heavy Duty three-in-one reflective insulation, thermal break and Class 2 Vapour Barrier. Trade Select™ ThermalLiner™ is suitable for use in roof, wall and floor applications. Designed to manage heat gain and heat loss, Trade Select™ ThermalLiner™ offers superior thermal performance to conventional insulation, and reduces thermal bridging and conductivity between building elements.


ThermalLiner™ is ideal for use in residential homes and commercial sheds.

- > Extra Heavy Duty
- > Flexible R0.1 reflective foam insulation liner
- > Low glare
- > High performance thermal insulation
- > Acoustic dampener
- > Low Flammability, suitable for all BALs in bushfire-prone areas

### Construction

Trade Select™ ThermalLiner™ consists of a 4 mm core of chemically cross-linked, closed-cell high-density XPE foam laminated with strong polymer weave and aluminium foil with reflectivity of 95% reflectivity and emissivity of 0.05 to one side and 97% and emissivity of 0.03 to the other.

Ametalin utilises Advanced Laminating Technology; the polymer adhesive remains tacky indefinitely and provides superior resistance to heat, fire and delamination.



### Total System R-Values

#### Shed Roof

5° pitched with no ceiling

Winter **R<sub>t</sub> 0.82**

Summer **R<sub>t</sub> 1.86**

#### Shed Wall

No lining

Winter **R<sub>t</sub> 0.95**

Summer **R<sub>t</sub> 0.91**

ThermalLiner has a material R-value of R0.1. When it is incorporated into typical construction systems, the following thermal performance can be achieved:

R-values apply to typical conditions for mainland Australian capital cities and have been calculated by an independent consulting engineer, in accordance with AS/NZS 4859.2:2018. For detailed design of building systems readers are advised to seek advice from a qualified engineer, based on actual site conditions.

The contributions of this product to the total system R-value depends on installation and environmental conditions.

## Material Properties and Classifications

ThermalLiner™ classifications in accordance with AS/NZS 4200.1:2017 and AS/NZS 4859.1:2018

Criteria	Reference	Result	Requirement
Flammability Index	AS 1530.2-1993	Low $\leq 5$	High ( $> 5$ ) / Low ( $\leq 5$ )
Material Thermal Resistance	ASTM C518	0.11 m <sup>2</sup> ·K/W (R <sub>M</sub> 0.1)	Value
Tensile Strength Machine Direction	AS 1301.448s-91	15.9 kN/m	Min 9.5 kN/m
Tensile Strength Lateral Direction	AS 1301.448s-91	14.6 kN/m	Min 6.0 kN/m
Edge Tear Machine Direction	TAPPI T 470 om-89	666 N	Min 65 N
Edge Tear Lateral Direction	TAPPI T 470 om-89	606 N	Min 65 N
Vapour Control	ASTM E96	Class 1 Vapour Barrier	Class 1 to 4
Vapour Permeance	ASTM E96	0.001 µg/N.s	Value
Water Control	AS/NZS 4201.4:1994	Water Barrier	Classification
Air Control	AS/NZS 4200.1:2017	Air Barrier	Classification
Resistance to Dry Delamination	AS/NZS 4201.1:1994	Pass	Pass
Resistance to Wet Delamination	AS/NZS 4201.2:1994	Pass	Pass
Shrinkage (Repeated wetting & drying)	AS/NZS 4201.3:1994	0.0%	< 0.5%
Electrical Conductivity	AS/NZS 4200.1:2017	Electrically Conductive	Classification
Emittance Value	AS/NZS 4201.5:1994	Anti-glare side: 0.05, Bright side: 0.03	Value
Emittance Classification	AS/NZS 4200.1:2017	IR Reflective, IR Reflective	Classification
Emittance Category	AS/NZS 4200.1:2017	RR	Category

## NCC Compliant

Trade Select™ ThermalLiner™ complies with AS/NZS 4859.1:2018 and AS/NZS 4200.1:2017, and therefore meets all of the requirements of the *National Construction Code of Australia* for insulation, pliable building membranes and sarking-type materials.

## Fire Performance

### Flammability Index

Low ( $\leq 5$ )

Tested in accordance with AS 1530.2-1993 *Methods for fire tests on building materials, components and structures Part 2: Test for flammability of materials*.

### Bushfire Attack Levels

Complies with AS 3959-2018 *Construction of buildings in bushfire-prone areas* for use in all BALs.

Seek independent advice regarding the selection of sarking prior to installation in the BAL design.

## Dimensions

1500 mm x 20 m (30 m<sup>2</sup>)

Nominal thickness: 4 mm

## Specification Notes

When specifying, state the following:

Product Name: Trade Select™ ThermalLiner™

The insulation to be installed shall be Trade Select™ ThermalLiner™ double sided reflective, fibre-free thermo-reflective insulation, comprised of cross-linked, closed-cell core XPE foam with anti-glare foil facing on one side and plain foil facing on the other side. Material R-value is R0.11 and shall be installed in accordance with AS 4200.2:2017 *Pliable Building Membranes and Underlays, Part 2: Installation*.

Emittance Value: 0.05, 0.03

Emittance Classification: IR Reflective, IR Reflective

Material Value: R0.11

Vapour Control Classification: Class 1 Vapour Barrier, 0.001 µg/N.s

Water Control Classification: Water Barrier

Duty: Extra Heavy in accordance with AS/NZS 4200.1:2017

Complete details available on our website:

<https://www.tradeselect.co/>

## Handling and Storage

Store this product under cover out of direct sunlight, in a clean dry place in the pack provided.

Durability may be affected by environmental factors, including chemical and airborne pollutants, if used in industrial or farm buildings.

Australian designed for Australian conditions. Manufactured by: Ametalin 9-11 Playford Crescent, Salisbury North SA 5108 T: +61 8 8285 6955 F: +61 8 8285 5911 E: info@ametalin.com

© 2024 Ametalin All Rights Reserved. Ametalin is a division of Amalgamated Metal Industries Pty. Ltd. Product information in this publication and otherwise supplied to users is based on our general experience and is given in good faith, but due to factors outside our knowledge and control which may affect the use of products, no warranty is given or implied with respect to this information or the product itself regarding the suitability of the product for any particular purpose. The usage of this and other building membranes will affect moisture migration in the building element. The purchaser should independently determine the suitability of the product for the intended purpose. For large projects with complex air-conditioning and condensation issues, designers may wish to contact our technical department. Product colour may vary from batch to batch. Amalgamated Metal Industries Pty. Ltd. reserves the right to amend product specifications without prior notice. Information provided is considered to be true and correct at the time of publication. Complete details including installation instructions are available on our website: [www.tradeselect.co](http://www.tradeselect.co) TPM-45576-1

Distributed by:	<b>NATIONAL DISTRIBUTOR</b>
	<b>RM INDUSTRIES</b>
	Phone: 1800 764 638
	Email: <a href="mailto:info@rmindustries.com.au">info@rmindustries.com.au</a>
	<a href="http://www.rmindustries.com.au">www.rmindustries.com.au</a>

